

a capacitor formed on the conductive film and comprising a first electrode, a ferroelectric film and a second electrode;

wherein the ferroelectric film includes at least one element selected from the group consisting of lead, barium and bismuth and formed from above the first electrode to above the insulating film;

wherein a reaction barrier film is provided between the insulating film and the ferroelectric film to prevent a reaction between the insulating film and the ferroelectric film, said reaction barrier film being in contact with a lower surface of said first electrode such that the reaction barrier film is interposed between the lower surface of the first electrode and said insulating film;

wherein a diffusion barrier film is provided between the conductive film and the first electrode and side faces of the diffusion barrier are not brought into contact with the ferroelectric film;

wherein an upper surface of said diffusion barrier film and an upper surface of said reaction barrier film are substantially on a same plane; and

wherein side faces of the first electrode are provided to be brought into contact with the ferroelectric film.

7. (Twice Amended) A semiconductor device comprising:

a substrate provided with a transistor;

an insulating film formed on the substrate and having an opening portion;

a conductive film formed in the opening portion; and

a capacitor formed on the conductive film and comprising a first electrode; a ferroelectric film and a second electrode;

wherein the ferroelectric film includes at least one element selected from the group consisting of lead, barium and bismuth and formed on an upper face and side faces of the first electrode and on the insulating film;

D2 wherein a reaction barrier film is provided between the insulating film and the ferroelectric film to prevent a reaction between the insulating film and the ferroelectric film, said reaction barrier film being in contact with a lower surface of said first electrode such that the reaction barrier film is interposed between the lower surface of the first electrode and said insulating film;

wherein a diffusion barrier film is provided between the conductive film and the first electrode and in the opening portion of the reaction barrier film; and

wherein an upper surface of said diffusion barrier film and an upper surface of said reaction barrier film are substantially on a same plane.

Please add new claim 30-33 as follows:

30. A semiconductor device comprising:

an insulating film formed on a substrate provided with a transistor and having an opening portion;

a conductive film formed in the opening portion;

D3 a capacitor formed on the conductive film and comprising a first electrode, a ferroelectric film and a second electrode, wherein the ferroelectric film includes at least one element selected from the group consisting of lead, barium and bismuth and formed from above the first electrode to above the insulating film; and

means for preventing a reaction between the insulating film and the ferroelectric film, said means for preventing a reaction being in contact with a lower surface of said first

electrode such that the means for preventing a reaction is interposed between the lower surface of the first electrode and said insulating film;

wherein a diffusion barrier film is provided between the conductive film and the first electrode and side faces of the diffusion barrier are not brought into contact with the ferroelectric film;

wherein an upper surface of said diffusion barrier film and an upper surface of said means for preventing a reaction are substantially on a same plane; and

wherein side faces of the first electrode are provided to be brought into contact with the ferroelectric film.

D3
31. A semiconductor device according to claim 30, wherein said means for preventing a reaction comprises a TiO_2 film.

32. A semiconductor device comprising:

a substrate provided with a transistor;

an insulating film formed on the substrate and having an opening portion;

a conductive film formed in the opening portion,

a capacitor formed on the conductive film and comprising a first electrode; a ferroelectric film and a second electrode, wherein the ferroelectric film includes at least one element selected from the group consisting of lead, barium and bismuth and formed on an upper face and side faces of the first electrode and on the insulating film; and

means for preventing a reaction between the insulating film and the ferroelectric film, said means for preventing a reaction being in contact with a lower surface of said first electrode such that the means for preventing a reaction is interposed between the lower surface of the first electrode and said insulating film;

wherein a diffusion barrier film is provided between the conductive film and the first electrode and in the opening portion of the means for preventing a reaction; and

D3 wherein an upper surface of said diffusion barrier film and an upper surface of said means for preventing a reaction are substantially on a same plane.

33. A semiconductor device according to claim 32, wherein said means for preventing a reaction comprises a TiO_2 film.
